

Soudafoam Fireblock

SOUDAL

- Type VB Residential Fireblock*
- Prevents the Spread of Flames and Smoke
- Orange Color
- Low Expansion Gun Foam
- High Yield
- Moisture Cure, One Component
- Excellent Adhesion on Most Building Materials
- No Shrinkage
- Exceptional Thermal Insulation
- Great Acoustical Insulation
- CFC-Free Propellants - Harmless to Ozone Layer
- UL Approved for ASTM E814 (modified)

* This product is not for use in firestop applications



**Penetrates Between
Floors & Walls
Electrical Outlets
Pipes & Vents**

This information and all further technical advice are based on SOUDAL present knowledge and experience. However, SOUDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SOUDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SOUDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SOUDAL reserves the right to make any changes according to technological progress or further developments.

Soudafoam Fireblock



| | |
|------------------------------------|---|
| Base | Polyurethane |
| Consistency | Stable foam |
| Curing system | Moisture-cure |
| Skin formation (68°F/65% R.H.) | 8 minutes |
| Drying time (68°F/65% R.H.) | Dust free after 20-25 minutes |
| Curing rate (68°F/65% R.H.) | 1 hour for a 1/8" bead |
| Shrink | None |
| Post expansion | None |
| Cellular structure | 70-80% closed cells |
| Specific gravity | 1.56 lbs/cubic foot (extruded, fully cured) |
| Temperature resistance | -40°F to +194°F once cured |
| Color | Orange |
| UL 1715 Fire Test | Flame Spread 15, Smoke Developed 35 |
| Insulation factor | 4.1 for 1 inch |
| Shear strength (ASTM C-273) | 8.70 psi |
| Compressive strength (ASTM D-1621) | 4.35 psi |
| Tear strength | 17.40 psi |
| Water absorption | 1% Volume |

(*) These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

Limitations:


- Excellent adhesion on most substrates, except for PTFE, PE and PP.
- Always store can with the valve pointed upwards.
- Cured PU foam must be protected from UV radiation.
- Lower temperature and humidity will extend curing time.

CAUTION:

KEEP OUT OF REACH OF CHILDREN. For professional use only. KEEP AWAY FROM HEAT (>49°F), SPARKS AND OPEN FLAME. DO NOT PUNCTURE OR INCINERATE CAN. DO NOT EXPOSE TO DIRECT SUNLIGHT. USE ONLY IN WELL VENTILATED AREAS. In case of eye contact, flush eye with water for 15 minutes and get immediate medical attention. For inhalation, move to fresh air. For skin contact, wash thoroughly with water and soap. If swallowed, drink large quantities of water, but do not induce vomiting. Call a physician immediately. Refer to SDS for further information.

PLEASE REFER TO TECHNICAL DATA SHEET FOR COMPLETE INFORMATION ABOUT THE PRODUCT

SODAL FEATURES



Distributed by: Soudal Accumetric • 350 Ring Road, Elizabethtown, KY 42701 • info@soudalusa.com • 877-873-8739 • www.soudalusa.com

SoudafoamFireblock.Combo/022421